

RECEIVED
CENTRAL FAX CENTER

JUL 07 2005

AMENDMENT UNDER 37 C.F.R. § 1.111
U.S. Appl. No.: 10/743,412
Attorney Docket No.: Q79133


AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:



LISTING OF CLAIMS:

1. (currently amended): An infrared-sensitive lithographic printing plate comprising a support and a heat-sensitive layer, ~~wherein~~ wherein the heat-sensitive layer comprises: (A) a copolymer having a monomer unit represented by the following formula (I); (B) an alkali-soluble high molecular weight compound having a sulfonamide group; and (C) a light-heat conversion material, and the copolymer (A) and the compound (B) are separate and distinct components:

Formula (I):



wherein R represents a hydrogen atom or an alkyl group; X represents an arylene group which may have a substituent, or any of the following structures:



BEST AVAILABLE COPY

AMENDMENT UNDER 37 C.F.R. § 1.111
U.S. Appl. No.: 10/743,412
Attorney Docket No.: Q79133

wherein Ar represents an arylene group which may have a substituent; Y represents a divalent connecting group.

2. (original): The infrared-sensitive lithographic printing plate according to claim 1, wherein the copolymer (A) comprises the monomer unit represented by formula (I) in an amount of 1 to 90 mol%

3. (original): The infrared-sensitive lithographic printing plate according to claim 1, wherein the copolymer (A) further has at least one monomer unit of (meth)acrylic acid esters, (meth)acrylamide derivatives and styrene derivatives.

4. (original): The infrared-sensitive lithographic printing plate according to claim 1, wherein the copolymer (A) further has at least one monomer unit of (meth)acrylic acid esters, (meth)acrylamide derivatives and styrene derivatives in an amount of 5 to 90 mol%.

5. (original): The infrared-sensitive lithographic printing plate according to claim 1, wherein the heat-sensitive layer comprises the copolymer (A) in an amount of 1 wt% to 40 wt%.

6. (original): The infrared-sensitive lithographic printing plate according to claim 1, wherein the alkali-soluble high molecular weight compound (B) has at least one monomer unit of low molecular weight compounds each having in one molecule, at least one sulfonamide group -NH-SO₂- and at least one polymerizable unsaturated bond.

7. (original): The infrared-sensitive lithographic printing plate according to claim 1, wherein the heat-sensitive layer further comprises novolak resin.

8. (original): The infrared-sensitive lithographic printing plate according to claim 1, wherein the light-heat conversion material is an infrared absorbing dye.

AMENDMENT UNDER 37 C.F.R. § 1.111
U.S. Appln. No.: 10/743,412
Attorney Docket No.: Q79133

9. (original): The infrared-sensitive lithographic printing plate according to claim 8, wherein the infrared absorbing dye has an absorbance at 700 to 1200 nm infrared rays.

10. (original): The infrared-sensitive lithographic printing plate according to claim 1, wherein the heat-sensitive layer comprises the light-heat conversion material in an amount of 0.01 to 50 wt%.

11. (new): The infrared-sensitive lithographic printing plate according to claim 1, wherein X in formula (I) is $-C(=O)-Y-$.

12. (new): The infrared-sensitive lithographic printing plate according to claim 1, wherein the copolymer (A) further has at least one monomer unit selected from the group consisting of (meth)acrylic acid esters and (meth)acrylamide derivatives.